

University of Parma Research Repository

ZnO nanoparticles with high degradation efficiency of organic dyes under sunlight irradiation

This is the peer reviewd version of the followng article:

Original

ZnÖ nanoparticles with high degradation efficiency of organic dyes under sunlight irradiation / Sanna, Vanna; Pala, Nicolino; Alzari, Valeria; Nuvoli, Daniele; Carcelli, Mauro. - In: MATERIALS LETTERS. - ISSN 0167-577X. - 162:(2016), pp. 257-260. [10.1016/j.matlet.2015.10.031]

Availability:

This version is available at: 11381/2807711 since: 2021-09-30T17:58:39Z

Publisher: Elsevier B.V.

Published DOI:10.1016/j.matlet.2015.10.031

Terms of use:

Anyone can freely access the full text of works made available as "Open Access". Works made available

Publisher copyright

note finali coverpage

(Article begins on next page)

Le Mans Journals

P-authorquery-vx

Our reference: MLBLUE 19687

AUTHOR QUERY FORM

	Journal: MLBLUE	Please e-mail your responses and any corrections to:
ELSEVIER	Article Number: 19687	E-mail: corrections.esch@elsevier.macipd.com

Dear Author,

Please check your proof carefully and mark all corrections at the appropriate place in the proof (e.g., by using on-screen annotation in the PDF file) or compile them in a separate list. Note: if you opt to annotate the file with software other than Adobe Reader then please also highlight the appropriate place in the PDF file. To ensure fast publication of your paper please return your corrections within 48 hours.

For correction or revision of any artwork, please consult http://www.elsevier.com/artworkinstructions.

Any queries or remarks that have arisen during the processing of your manuscript are listed below and highlighted by flags in the proof. Click on the \underline{Q} link to go to the location in the proof.

Your article is registered as a regular item and is being processed for inclusion in a regular issue of the journal. If this is NOT correct and your article belongs to a Special Issue/Collection please contact <u>j.mohideen@elsevier.com</u> immediately prior to returning your corrections.

Location in article	Query / Remark: <u>click on the Q link to go</u> Please insert your reply or correction at the corresponding line in the proof
<u>Q1</u>	Please confirm that given names and surnames have been identified correctly and are presented in the desired order.
<u>Q2</u>	Please check and confirm if the address for the corresponding author that has been added here is correct.

Thank you for your assistance.



Materials Letters **()**



Mater Lett (2015), http://dx.doi.org/10.1016/j.matlet.2015.10.031

Contents lists available at ScienceDirect

Materials Letters



© 2015 Published by Elsevier B.V.

journal homepage: www.elsevier.com/locate/matlet

agents for decomposition of dyes under solar light exposure.

ZnO nanoparticles with high degradation efficiency of organic dyes under sunlight irradiation

¹⁵ Qi Vanna Sanna^{a,b,*}, Nicolino Pala^b, Valeria Alzari^c, Daniele Nuvoli^c, Mauro Carcelli^d

ABSTRACT

a Laboratory of Nanomedicine, Department of Chemistry and Pharmacy, University of Sassari, c/o Porto Conte Ricerche, Tramariglio, 07041 Alghero, Italy

wastewater containing azo dyes.

^b Department of Chemistry and Pharmacy, University of Sassari, 07100 Sassari, Italy

^c Department of Chemistry and Pharmacy, and Local Unit INSTM, University of Sassari, 07100 Sassari, Italy

^d Department of Chemistry, University of Parma, Parco Area delle Scienze 17/A, 43124 Parma, Italy

ARTICLE INFO

24 Article history: 25 Received 28 July 2015 26 Received in revised form 3 October 2015 27 Accepted 7 October 2015 28 29

1. Introduction

Keywords: ZnO

- Nanoparticles Sunlight
- Photocatalysis

34 35

36 37 38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58

59

60

61

62

63

30

31

32

33

1

2 3

4 5 6

12

13 14

16

17

18

19

20 21 22

23

In order to decrease the damage caused by dye pollution to environment and human, the use of photocatalysts to convert organic compounds in contaminated water into nontoxic chemicals has been extensively investigated [1,2].

Recently, titanium dioxide (TiO₂) and zinc oxide (ZnO) nanoparticles are emerged as successful alternatives to conventional methods for the degradation of non-biodegradable pollutants [3,4]. TiO₂ is the most studied and used owing to its chemical and thermal stability, low cost, and nontoxicity. The basic principle of semiconductor photocatalysis involves photogenerated electrons and holes migrating to the surface that reduce and oxidize the adsorbed reactants, leading to the pollutant decomposition [5]. However, two types of defects limit the photocatalytic reactivity of such material: the excitation/activation by high energy UV irradiation and a low quantum yield rate, which resulted from a low rate of electron transfer to oxygen and a high rate of recombination between excited electron/hole pairs [6]. The electron-hole pairs can be formed by UV light at wavelength shorter than 387 nm, thus, only a small portion of the solar spectrum can be used for photooxidation reaction using TiO₂ [7]. In order to absorb visible light by increasing the charge separation and thus improve

E-mail address: vsanna@uniss.it (V. Sanna).

- 64 http://dx.doi.org/10.1016/j.matlet.2015.10.031
 - 0167-577X/© 2015 Published by Elsevier B.V.
- 65 66

the photodegradation, TiO_2 was doped by metal ions [8]. Besides, band gap narrowing of TiO₂ can be better achieved by using anionic dopants that enhance the thermal stability of catalyst [9].

ZnO nanoparticles were fabricated by a simple and low cost precipitation method as photocatalytic Q2

The ZnO nanoparticles showed excellent photodegradation efficiency and good recycling perfor-

mance, supporting the potential application as economical and a highly sunlight-active material to treat

In this scenario, ZnO nanoparticles have been emerged as a valid alternative to TiO₂ for the photodecomposition of organic pollutants and dyes [10,11], due to their ability to generate H₂O₂ more efficiently than TiO₂. This is directly related to a larger number of active sites with high surface reactivity [12], the relatively high band gaps (3.3 eV) at room temperature and the large exciton binding energy (60 meV). ZnO absorbs over a large fractions of solar spectrum than other photocatalysts, and remove organic contaminants under visible irradiation [13]. ZnO nanoparticles can be synthesized by various approaches [14], but the obtained nanoparticles are prone to aggregate due to the large surface area and high surface energy. In spite of this, and in order to also improve their water dispersion [15], other methods for the preparation of ZnO are expected.

Herein, we proposed a simple and economical precipitation method to prepare stable ZnO nanoparticles as catalysts with high photodegradation capacity under solar light irradiation and good recycling performance.

2. Experimentals

The detailed experimental procedures are described in Supporting information.

Please cite this article as: V. Sanna, et al., ZnO nanoparticles with high degradation efficiency of organic dyes under sunlight irradiation, Mater Lett (2015), http://dx.doi.org/10.1016/j.matlet.2015.10.031

^{*} Corresponding author at: Laboratory of Nanomedicine, Department of Chemistry and Pharmacy, University of Sassari, c/o Porto Conte Ricerche, Tramariglio, 07041 Alghero, Italy. Fax: +39 079 229 559.

1

2

3

4

5

6

7

8

9

10

11

12

13

14

15

3. Results and discussion

ZnO nanoparticles with a mean diameter of 41.7 ± 8.2 nm, PI of 0.132 ± 0.04 (Fig. 1a), and spherical shape (Fig. 1b) were successfully prepared by a modified precipitation method [16].

The XRD pattern of the nanoparticles (Fig. 1c) can be well indexed to hexagonal wurtzite structural ZnO (JCPDS card no. 36-1451). The average crystalline size, calculated from the XRD pattern by using the Debye-Scherrer formula [17], was found to be 36 nm.

As shown in Fig. 1d, the exciton absorption at 378 nm represents the characteristic single peak of hexagonal ZnO nanoparticles [18]. The calculated E value was 3.4 eV, very close to the band gap of intrinsic ZnO powder [19].

Fig. 2a shows typical UV–Vis spectrum of methyl orange (MO, 10 mg/L), in the presence of ZnO catalyst (100 μ g/mL) at different irradiation times. As it can be seen, the intensity of the peak at 462 nm progressively decreases until it disappears almost completely within 60 min irradiation time. Furthermore, without the presence of either catalyst or the UV radiation, for all considered times, any change in the absorbance values was not observed. These results can be explained based on the large band gap value that delays the process of electron-hole recombination, which significantly increases the photocatalytic activity [1,20].

To determine the effect of catalyst loading, the experiments were performed without ZnO, and in the presence of different catalyst concentrations (0.05–0.75 mg/mL) for a fixed dye solution (10 mg/L), at pH 9.0, for 2 h. As depicted in Fig. 2b, both in the darkness and in the absence of ZnO the MO photodegradation was negligible. Conversely, the photocatalytic ability of the nanoparticles is strongly related to the increasing of catalyst-loading such as to the irradiation time. The MO degradation resulted of

47%, and 82%, in the presence of 0.05 and 0.1 mg/mL of ZnO, respectively, after irradiation for 60 min. At higher ZnO concentrations, the complete MO decolorization has been reached within 45 min. The increase of the photocatalyst loading determines an increased number of active sites and, consequently, leads to enhanced production of OH• radicals, increasing the percentage of photodegradation [21]. On the other hand, the increase of ZnO concentration over 0.25 mg/mL does not determine a linear increase in photocatalytic efficiency, due to a decrease in UV light penetration as a result of light scattering effect.

67

68

69

70

71

72

73

74

75

76

77

78

79

80

81

82

83

84

85

86

87

88

89

90

91

92

93

94

95

96

97

98

To study the pH effect on the decolorization efficiency, experiments were performed in pH range 3-11, at a constant dye concentration (10 mg/L), and catalyst loading of 0.1 g/L, for 60 min. With the enhance of the pH from 3 to 5 a fast increase of decolorization was observed (from 66.2% to 80.4%), followed by a gradually increase at pH 7 (85.5%), and the maximum value at pH 9 (90.3%) (Fig. 2c). A further increase to pH 12, instead, determined a reduction of degradation efficiency (82%) related to zero point charge of ZnO (9.0 ± 0.3). More specifically, below pH 9, the ZnO surface is positively charged and covered by the dye molecules. Above this pH, the surface, negatively charged by adsorption of hydroxide ions, favors the formation of OH•, thus enhancing the photodegradation efficiency [1,20].

The influence of initial MO concentration on the degradation efficiency was studied by varying the dye concentration (5.0-25.0 mg/L), under pH 9, and ZnO nanoparticles (100 μ g/mL) as constant, until 120 min of irradiation time. With the increase of initial dye concentration, the degradation decreases remarkably (Fig. 2d). After 60 min, the decolorization efficiencies were found 53.6, 62.4, 76.8, 82.3, and 86.6% for MO concentration of 25, 15, 10, 7.5, and 5.0 mg/L, respectively. The almost complete degradation of MO occurred at 120 min for the highest MO concentrations,



Fig. 1. (a) Particle size distribution, (b) TEM image, (c) XRD pattern, and (d) UV-vis spectrum of ZnO nanoparticles.

ARTICLE IN PRESS

V. Sanna et al. / Materials Letters **(()**



the ZnO nanoresence of ZnO on of log C_0/C_t vs parison of decoingly, at the ecolorization er (10 mg/L), of fabricated e irradiation

Fig. 2. (a) UV–vis spectrum of MO solution (10 mg/L) as a function of irradiation time in the presence of ZnO nanoparticles (0.1 mg/mL); (b) Influence of the ZnO nanoparticles concentration on decolorization of MO solutions for 60 min of exposure; (c) Influence of the pH on decolorization of MO solutions in the presence of ZnO nanoparticles (0.1 mg/mL); (d) Influence of the MO concentration on decolorization rate in the presence of ZnO nanoparticles (0.1 mg/mL); (e) Linear variation of log C_0/C_t vs time for the photocatalytic degradation of MO at different initial concentrations (5.0–25 mg/L) in the presence of 0.1 mg/mL ZnO nanoparticles; (f) Comparison of decolorization of MO solution (10 mg/L) and in three successive cycles of exposure (ZnO nanoparticles 0.1 mg/mL; under pH 9).

after 90 min for 10 and 7.5% mg/L concentrations, and 75 min for lowest dye concentration (5 mg/L).

As previously reported, the high MO concentration determines a competition between dye and OH⁻ ion adsorption on the catalyst surface. The presence of dye depresses the OH⁻ ion adsorption, resulting in the reduction on the OH[•] formation. Additionally, with increased dye molecules the solution became more intense colored and the path length of photons entering the solution decreased [1,2].

To date, only a handful studies have been attempted to evaluate the photodegradation efficiency of ZnO catalysts for organic MO dye under solar light exposure. It is reported that ZnO photocatalyst at a dose of 1 g/L, determined a complete degradation of 25 mg/L MO solutions within 90 min [22]. Interestingly, at the same MO concentration and time, we found 77% of decolorization efficiency by using a catalyst dose ten times lower (10 mg/L), suggesting an excellent photodegradation activity of fabricated nanoparticles.

To obtain the reaction kinetics, the $\log C_0/C_t$ vs the irradiation time was plotted, giving straight lines that indicate first order re-actions (Fig. 2e). The corresponding parameters k and the corre-lation coefficient (R) of the decolorization process are summarized in Table 1. According to literature, the reaction rate constant de-creases with increasing initial dye concentration [7]. The organic MO is first adsorbed on the surface of the nanoparticles and then degradation occurs under irradiation. As the initial the

Please cite this article as: V. Sanna, et al., ZnO nanoparticles with high degradation efficiency of organic dyes under sunlight irradiation, Mater Lett (2015), http://dx.doi.org/10.1016/j.matlet.2015.10.031

ARTICLE IN PRESS

V. Sanna et al. / Materials Letters ■ (■■■) ■■■-■■

 Table 1

 Pseudo-first order apparent constant values for the different initial concentrations of MO.

MO concentration (mg/L)	$k ({ m min}^{-1})$	R ²
25	0.0160	0.9741
15	0.0210	0.9718
10	0.0334	0.9617
7.5	0.0372	0.9649
5.0	0.0408	0.9333

concentration of MO increases, the molecules aggregate on the catalyst surface resulting in quenching of the excited molecules [8].

As illustrated in Fig. 2f, the photodegradation efficiency shares an overlapping behavior in each of the successive cycles, suggesting that nanoparticles were reusable and retain a good photodegradation efficiency.

4. Conclusions

In this study, ZnO nanoparticles have been obtained by a simple and low cost precipitation method.

Results demonstrated the importance of modulating the optimum degradation parameters, and the ability to setup a favorable combination suitable to obtain a high degradation rate. ZnO nanopowders possess excellent photocatalytic activity under sunlike irradiation for decolorization of MO, and retain a good recycling performance, suggesting that may be applied as an economical and highly sunlight-active material to treat wastewater containing azo dyes.

Appendix A. Supplementary material

Supplementary data associated with this article can be found in the online version at doi:10.1016/j.matlet.2015.10.031.

References

- [1] H. Wang, C. Xie, W. Zhang, S. Cai, Z. Yang, Y. Gui, J. Hazard Mater. 141 (2007) 645.
- [2] K. Byrappa, A.K. Subramani, S. Ananda, K.M. Lokanatha Rai, R. Dinesh, M. Yoshimura, Bull. Mater. Sci. 29 (2006) 433.
- [3] H. Tian, J.F. Ma, K. Li, J.J. Li, Mater. Chem. Phys. 112 (2008) 47.
- [4] L. Andronic, A. Duta, Mater. Chem. Phys. 112 (2008) 1078.
- [5] K.M. Parida, N. Sahu, N.R. Biswal, B. Naik, A.C. Pradhan, J. Colloid Interf. Sci 318 (2008) 231.
- [6] C. Chen, J. Liu, P. Liu, B. Yu, Adv. Chem. Eng. Sci. 1 (2011) 9.
 [7] Y. Zhou, G. Jiang, R. Wang, X. Wang, R. Hu, X. Xi, J. Fiber Bioeng. Inform. 5
- (2012) 181.
- [8] X.B. Chen, S.S. Mao, Chem. Rev. 107 (2007) 2891.
- [9] J.C. Yu, W. Ho, J. Yu, H. Yip, P.K. Wong, J. Zhao, Environ. Sci. Technol. 39 (2005) 1175.
- [10] N. Serpone, P. Maruthamuthu, P. Pichat, E. Pelizzetti, H. Hidaka, J. Photochem. Photobiol. A: Chem 85 (2001) 247.
- [11] K. Kabra, R. Chaudhary, R. Sawhney, Ind. Eng. Chem. Res. 43 (2004) 7683.
- [12] C. Lizama, J. Freer, J. Baeza, H.D. Mansilla, Catal. Today 76 (2002) 235.
- [13] N.D. Salari, A.R. Khataee, J. Photochem. Photobiol. A 162 (2004) 317.
- [14] A. Koodziejczak-Radzimska, T. Jesionowski, Materials 7 (2014) 2833.
- [15] R. Hong, T. Pan, J. Qian, H. Li, Chem. Eng. J. 119 (2006) 71.
- [16] V. Alzari, V. Sanna, S. Biccai, T. Caruso, A. Politano, N. Scaramuzza, M. Sechi, D. Nuvoli, R. Sanna, A. Mariani, Compos. Part B Eng. 60 (2014) 29.
- [17] B.D. Cullity, Elements of X-ray Diffraction, Addison-Wesley, Reading, MA, 1978.
- [18] H. Zhang, D. Yang, S. Li, X. Ma, Y. Ji, J. Xu, D. Que, Mater. Lett. 59 (2005) 1696.
- [19] J. Tauc, R. Grigorovichi, A. Vancu, Phys. Status Solidi 15 (1966) 627.
- [20] S. Kansal, N. Kaur, S. Singh, Nanoscale Research Letters, 4 (20099 709).
- [21] M. Fox, M. Dulay, Chem. Rev. 93 (1993) 341.
- [22] S.K. Kansal, M. Singh, D. Sud, J. Hazard Mater. 141 (2007) 581.