



UNIVERSITÀ DI PARMA

ARCHIVIO DELLA RICERCA

University of Parma Research Repository

Special issue on voltage control of nanomagnetism

This is the peer reviewed version of the following article:

Original

Special issue on voltage control of nanomagnetism / Hu, J.; Ghidini, M.. - In: JOURNAL OF PHYSICS D. APPLIED PHYSICS. - ISSN 0022-3727. - 54:1(2021), p. 010201. [10.1088/1361-6463/abb9d4]

Availability:

This version is available at: 11381/2882335 since: 2022-01-19T07:38:29Z

Publisher:

IOP Publishing Ltd

Published

DOI:10.1088/1361-6463/abb9d4

Terms of use:

Anyone can freely access the full text of works made available as "Open Access". Works made available

Publisher copyright

note finali coverpage

(Article begins on next page)

03 August 2024

Preface on a Special issue on Voltage Control of Nanomagnetism

Jiamian Hu,¹ Massimo Ghidini^{2,3,4*}

¹Department of Materials Science and Engineering, University of Wisconsin-Madison, Madison, WI, 53706, USA

²Department of Mathematics, Physics and Computer Science, University of Parma, 43124 Parma, Italy.

³Diamond Light Source, Chilton, Didcot, Oxfordshire, OX11 0DE, UK.

⁴Department of Materials Science, University of Cambridge, Cambridge, CB3 0FS, UK.

(Please insert your affiliations)

E-mails: jhu238@wisc.edu (Please insert your email address) massimo.ghidini@unipr.it

Electric field is easier to localize than magnetic field and is non-power-dissipating in contrast to electric current. Therefore, using an electric voltage to control magnetism enables developing low-power, on-chip magnetic devices for a wide variety of potential applications such as data storage, non-von Neumann computing, and cell manipulation. Voltage control of magnetism has commonly been demonstrated in a magnetolectric heterostructures that integrates comprise a magnetic thin film and or nanostructure with a dielectric layer. Depending on the functional responses of the dielectric to applied voltage, voltage control of magnetism can be achieved through a number of routes, mediated by strain, charge, exchange bias, or redox reaction. This special issue covers the latest computational and experimental developments in the field of voltage control of magnetism, with a strong focus on the nanoscale phenomena. These works outline evidence at least four opportunities key research objectives which show great promise both for continued discovery for novel of fundamental science and creation of new technology concepts.

Precise control of ferroelectric domain switching. Strain-mediated voltage control of magnetism is achieved in heterostructures where the dielectric layer is a ferroelectric material that transmits sizeable strains (produced by ferroelectric domain switching) to an overlying magnetic film. First opportunities can arise from a precise control of ferroelectric domain switching (when the dielectric layer is also ferroelectric) and thereby the magnetization switching in the overlying magnet. Ferroelectrics can display complex polarization domain patterns and kinetic switching paths as voltage is applied. This complexity can induce can result in complex strain distributions which in turn complicate the magnetic switching. In this special issue, Pati and Taniyama [1] reported the coexistence of hysteresis-like and butterfly-like behaviors in the magnetization vs. voltage curves measured using Kerr microscopy in a (La,Sr)MnO₃ film on a ferroelectric lead magnesium niobate-lead titanate (PMN-PT) single crystal. This mixed feature is attributed to the coexisting 71°, 109°, and 180° ferroelectric domain switching in the rhombohedral PMN-PT. A thorough understanding of how local polarization switching influences local magnetization switching requires *in situ* imaging of both ferroelectric and magnetic domains in 3D and even 4D (time) under zero magnetic field, which is still under active research.

Voltage control of topologically non-trivial spin textures (vortices and skyrmions). Second opportunities can arise from voltage control of spin texture. Compared to voltage-controlled switching of average magnetization, voltage control of spin textures, including both topologically

ha formattato: Tipo di carattere: Corsivo

ha formattato: Tipo di carattere: Corsivo, Colore carattere: Automatico

Formattato: Allineato al centro, Rientro: Sinistro: 0 cm, Prima riga: 0 cm, SpazioPrima: 3 pt, Interlinea: singola

ha formattato: Tipo di carattere: Corsivo

ha formattato: Tipo di carattere: Corsivo, Apice

ha formattato: Tipo di carattere: Corsivo, Colore carattere: Automatico

ha formattato: Tipo di carattere: Corsivo

ha formattato: Tipo di carattere: Corsivo, Non Apice / Pedice

ha formattato: Tipo di carattere: Corsivo, Colore carattere: Automatico

Commentato [MG1]: I think it would look better with a reference for each of these items...or if not possible we should make it clear they are possibilities..

Commentato [JH2R1]: I checked the earlier published prefaces in JPhysD. I found that they only cite papers published on JPhysD, not from other journals. For example,

<https://doi.org/10.1088/1361-6463/aaf9d5>
<https://doi.org/10.1088/1361-6463/aa8d41>

Commentato [MG3]: Is this really a "or"? The next sentence only discusses one case-"dielectric", making the reader think that this "or" should be an "and", implying that to achieve VCM we always need a magnetic film and some sort of dielectric. Do I understand correctly?

Commentato [MG4]: Here as well we could cite a key paper for each.

Commentato [JH5R4]: Shall we check with the JPhysD whether citing papers in the prefaces are ok?

I think citing only 1 paper for each mechanism is likely not enough, but citing too many papers here won't look good for a preface article either?

ha formattato: Tipo di carattere: Corsivo

Commentato [MG6]: I think it is a good idea to group papers along 4 key points. However, the structure as it is is perhaps not very readable as the paragraphs are long, and usually the use of "First" etc, works well on short paragraphs. How about writing the titles for each section.

Commentato [MG7]: The title reflects the papers discussed.

Commentato [JH8R7]: The section titles look great!

ha formattato: Tipo di carattere: Corsivo

trivial (e.g., domain walls) and nontrivial (e.g., vortices, skyrmions) ones, is less explored. In this special issue, Ghidini *et al.* [2] used photoemission electron microscopy to simultaneously image the ferroelectric domains at the surface of a BaTiO₃ single crystal and the magnetic vortices in micrometer-sized Ni disks as DC voltage is applied to BaTiO₃. By varying the in-plane sample orientation, they were able to construct high-spatial-resolution vector maps of local magnetization at zero magnetic field under different voltages. The vector maps show the displacement of magnetic vortex cores driven by the voltage. The translation of vortex core is attributed to the change in the asymmetric strain distribution caused by the motion of 90° ferroelectric domain walls at the BaTiO₃ surface. This interpretation is corroborated by the authors' own micromagnetic simulations, and consistent with the micromagnetic modeling by Azaceta *et al.* [3] investigating the effect of strain gradient symmetry on vortex core translation.

Magnetic skyrmions, which typically have a topological charge number Q of ± 1 (c.f., $Q = \pm 0.5$ for vortices), have been intensively studied since the late 2000s. However, research into voltage control of magnetic skyrmions has not appeared until recently. Using micromagnetic simulations, Mehmood *et al.* [4] investigated strain-induced transition between magnetic skyrmion and other topological spin textures [in the Pt/Co/Ir trilayer nanodisk](#) through the modification of magnetoelastic anisotropy. Strain may also modify the strength of the interfacial Dzyaloshinskii-Moriya interaction (DMI) which is critical for stabilizing Néel-type skyrmions. The effects of strain-induced change in DMI on the thermodynamic stability and switching kinetics of the skyrmion deserve further study. Moreover, Rushforth *et al.* [5] propose a promising method to drive the motion of different types of topological spin textures including skyrmions. Combining micromagnetic and finite-element modeling, they predicted that sequential strain pulses from a piezoelectric layer can drive a deterministic motion of domain wall in an overlaying magnetic nanowire. Another promising method to drive the motion of skyrmions is to apply surface acoustic waves (SAWs). Notably, when the SAWs frequency is near the ferromagnetic resonance (FMR) frequency of the magnet, the resonant magnon-phonon coupling may facilitate the skyrmion manipulation. The physical principles of SAWs-driven excitation of FMR are reviewed by Puebla *et al.* [6]. Strain is, of course, not the only means for controlling skyrmions. In this special issue, Gu *et al.* [7] experimentally demonstrated a charge-mediated voltage control of the topological Hall effect (a fingerprint of DMI) in ultrathin SrRuO₃ films grown on (001)SrTiO₃ substrate. The authors' first-principle calculations reveal the presence of DMI at the SrRuO₃/SrTiO₃ interface where the tilted RuO₆ octahedra breaks the inversion symmetry. This work suggests opportunities for realizing voltage control of DMI and hence the skyrmions in all-oxide heterostructures.

[Voltage control of phase transitions and chemical reactions in a magnetic film](#). FeRh alloys display competing ground states of ferromagnetic (FM) and antiferromagnetic (AFM) structural phases. Upon cooling, AFM phase nucleates and grows from the parent FM phase, and the volume fractions of both phases vary continuously. Since such a phase transition is extremely sensitive to strain, it is possible to exploit voltage-induced strains from a piezoelectric substrate for *in situ* tuning the microstructure of a FeRh thin film and the associated magnetic properties. Fina and Fontcuberta [8] reviewed the achievements along this direction. In parallel, Nichterwitz *et al.* [9] demonstrated the possibility to control the direction of the redox reaction between a paramagnetic FeOOH and ferromagnetic Fe through the voltage-modulation of OH⁻ concentration in alkaline

aqueous electrolytes. Such ON/OFF switching of magnetization by liquid electrolyte gating offers new opportunities for the applications of magneto-electronic devices.

Exploiting dipolar interactions for voltage control of nanomagnetism. Zhou *et al.*[10] considered two coupled CoFeB nanoislands grown on a (001) PMN-PT ferroelectric substrate. Using phase-field simulations, they demonstrated that the dipolar interaction assists a voltage-induced full 180° switching in each nanoisland, an event which is fundamentally challenging to achieve because voltage does not break the time-reversal symmetry. Nomura *et al.*[11] considered an array of single-domain nanomagnets coupled via dipolar interactions. Using micromagnetic simulations, they demonstrated that the array can be exploited for realizing reservoir computing: the magnetization of each nanomagnet represents a node state of the reservoir, which can be updated through voltage-induced magnetization switching. Finally, Chen *et al.* [12] explored a different downstream task of voltage-induced magnetization switching in nanomagnets, by modeling how the associated change in magnetic stray field drives the motion of an adjacent magnetic nano-bead. This scheme is potentially useful for biological applications such as cell manipulation.

Looking ahead, we expect the field of voltage control of magnetism will continue to grow and that the research objectives outlined in this special issue will attract considerable interest. Moreover, we expect exciting science from the intertwining of voltage control of magnetism with the latest developments in other fields, such as two-dimensional ferroic materials, neuromorphic spintronics, nano-bio interfaces, and beyond.

References

- [1] Pati S P and Taniyama T 2019 Voltage-driven strain-induced coexistence of both volatile and non-volatile interfacial magnetoelectric behaviors in LSMO/PMN-PT (0 0 1) *J. Phys. D: Appl. Phys.* **53** 54003
- [2] Ghidini M, Pellicelli R, Mansell R, Pesquera D, Nair B, Moya X, Farokhipoor S, Maccherozzi F, Barnes C H W, Cowburn R P, Dhesi S S and Mathur N D 2020 Voltage-driven displacement of magnetic vortex cores *J. Phys. D: Appl. Phys.* **53** 434003
- [3] Azaceta I, Rae I W and Cavill S A 2019 Effect of strain gradient symmetry on vortex core translation *J. Phys. D: Appl. Phys.* **52** 454004
- [4] Mehmood N, Song X, Tian G, Hou Z, Chen D, Fan Z, Qin M, Gao X and Liu J-M 2019 Strain-mediated electric manipulation of magnetic skyrmion and other topological states in geometric confined nanodiscs *J. Phys. D: Appl. Phys.* **53** 14007
- [5] Rushforth A W, Rowan-Robinson R and Zemen J 2020 Deterministic magnetic domain wall motion induced by pulsed anisotropy energy *J. Phys. D: Appl. Phys.* **53** 164001
- [6] Puebla J, Xu M, Rana B, Yamamoto K, Maekawa S and Otani Y 2020 Acoustic ferromagnetic resonance and spin pumping induced by surface acoustic waves *J. Phys. D: Appl. Phys.* **53** 264002
- [7] Gu Y, Wei Y-W, Xu K, Zhang H, Wang F, Li F, Saleem M S, Chang C-Z, Sun J, Song C, Feng J, Zhong X, Liu W, Zhang Z, Zhu J and Pan F 2019 Interfacial oxygen-octahedral-tilting-driven electrically tunable topological Hall effect in ultrathin SrRuO₃ films *J. Phys. D: Appl. Phys.* **52** 404001
- [8] Fina I and Fontcuberta J 2019 Strain and voltage control of magnetic and electric properties of FeRh films *J. Phys. D: Appl. Phys.* **53** 23002
- [9] Nichterwitz M, Neitsch S, Röher S, Wolf D, Nielsch K and Leistner K 2019 Voltage-

Commentato [MC9]: Do we mean virtually impossible for fundamental reasons?

Commentato [JH10R9]: I made some changes.

controlled ON switching and manipulation of magnetization via the redox transformation of β -FeOOH nanoplatelets *J. Phys. D. Appl. Phys.* **53** 84001

- [10] Zhou M-J, Yang T, Wang J-J, Chen L-Q and Nan C-W 2019 Electric-field-controlled magnetization switching in multiferroic heterostructures containing interactive magnetic nanoislands *J. Phys. D. Appl. Phys.* **53** 24002
- [11] Nomura H, Furuta T, Tsujimoto K, Kuwabiraki Y, Samura N, Tamura E, Goto M, Nakatani R, Kubota H and Suzuki Y 2019 Randomly generated node-state-update procedure for dipole-coupled magnetic reservoir computing with voltage control of the magnetism *J. Phys. D. Appl. Phys.* **53** 94001
- [12] Chen C, Sablik J, Khojah R, Domann J, Dyro R, Hu J, Mehta S, Xiao Z (Maggie), Candler R, Carman G and Sepulveda A 2020 Voltage manipulation of magnetic particles using multiferroics *J. Phys. D. Appl. Phys.* **53** 174002